

# Technical Data LOOSE-LAY COLLECTION



## LOOSE-LAY/55

Covering type in accordance with EN ISO 10582	Heterogeneous Planks/Tiles, type 1
Number of colours	8 Planks / 2 Tiles
Pack. Unit/Pallet	914x183 mm: 1.67 m <sup>2</sup> /125.25 m <sup>2</sup> 457x457 mm: 1.67 m <sup>2</sup> /120.24 m <sup>2</sup> 600x600 mm: 1.80 m <sup>2</sup> /129.60 m <sup>2</sup>
Performance classification EN ISO 10582 / ISO 10874	23, 33, 42
Total thickness ISO 24346	4.2 mm
Wear layer thickness ISO 24340	0.55 mm
Surface treatment	yes/PU
Bevelled edges	yes
Total weight ISO 23997	7.23 kg/m <sup>2</sup>
Residual indentation ISO 24343-1	≤ 0.1 mm*
Dimensional stability ISO 23999	≤ 0.15 %*
Castor chair suitability ISO 4918	suitable for castor chairs in acc. with EN 12529, type W
Underfloor heating EN 1264-2	suitable (up to 28°C)
Behaviour to fire EN 13501-1	Bfl-s1
Resistance to thermal conductivity ISO 8302 / EN 12667	0.02 m <sup>2</sup> K/W
Electrical propensity when walked upon EN 1815	< 2 k/V
Impact sound improvement ISO 10140-3	6 dB
Colour fastness to artificial light ISO 105-B02/2	≥ 7
Electrostatic characteristics EN 1081	> 10 <sup>12</sup>
Chemical resistance ISO 26987	conforms**
Slip resistance	R9 to R10 (depending on design resp. emboss: details available on request)
Maintenance/Cleaning recommendation	Dr. Schutz

\* Averaged value

(Date: 01/01/2023)

\*\* Vis-à-vis the short-term effects of normal, domestic agents.

Please also note the installation and cleaning and care instructions.

